



GENERAL FINISHES

2462 Corporate Circle East Troy, WI 53120
800-783-6050 Fax 262-642-4707

Water Base

Enduro CLEAR ACRYLIC

Classification:

Water Based Acrylic Finish

Product Description:

Enduro CLEAR ACRYLIC is a high performing commercial grade acrylic topcoat with superior clarity & hardness. Designed for interior use on furniture, cabinets, & mill-work, it exhibits excellent water and chemical resistance, Enduro CLEAR ACRYLIC builds exceptionally well. Designed for spray applications, it dries rapidly, and flows and levels to produce a smooth, uniform, beautiful finish.

Enduro CLEAR ACRYLIC is VOC-Compliant, low odor, non-flammable, and will clean-up with soap and water. It is self-sealing, however General Finishes Enduro Sealer is recommended to provide optimum finish quality.

For additional chemical, water, & abrasion resistance, add General Finishes Enduro Crosslinker.

Application:

HVLP: Accuspray Guns recommended. Use a 0.43" (1.1 mm) nozzle / tip assembly & #9 Air Cap. Airless: 0.009"—0.011" tip. Allow 30 minutes -2 hours dry before sanding (temperature / humidity dependent). Sand with #220 or finer between coats. 2 - 4 coats recommended.

Product Data:

- Density: 8.5 +/- 0.2 lbs.
- Weight Solids: 29—31%
- Volume Solids: 27—29%
- Viscosity: 30 - 40 seconds
Method: Ford #4 @ 77 F.
- pH: 7.5 - 8.5
- V.O.C.: 270 g/l (2.26 lbs/gal)
excluding water
- % VOC: 13%
- % HAPS: 5.4%
- Storage: Protect from Freezing

Container:

Gallons, 5-gal Pails, and 55-gal Drums

Sheen:

Flat (10), Satin (35), Semi-Gloss (60),
Gloss (90)

Dry Time 70°F and 70% R.H:

- Dry: 10 - 20 minutes
- To Sand: 30 minutes -2 hours

GENERAL FINISHES

"The Country's Finest Full Line Manufacturer of Wood Finishing Products"

www.generalfinishes.com



GENERAL FINISHES

2462 Corporate Circle, East Troy, WI 53120 800-783-6050

Mixing and Application:

- Catalyst Ratio: 3 oz / gal GF Crosslinker if desired
- Pot Life: 24 Hours with catalyst
- Shelf Life: 1 year, minimum
- Reducer/Thinner: EF Extender (10 –20%) if needed

Stain & Sealer Recommendation:

Can be used over most water base and solvent base stains. For best results and superior color and adhesion, General Finishes EF Water Base Stains and GF Oil Base Stains are recommended. Allow stains to dry thoroughly before topcoating.

Enduro CLEAR ACRYLIC may be used over most solvent base and water base paints. Allow paints to dry before thoroughly before topcoating.

Enduro CLEAR ACRYLIC is designed to be self-sealing. However General Finishes EF Sanding Sealer should be used for optimal performance and appearance.

Surface Preparation:

Surface must be clean, dry, and free of all contaminants. Sand with 220 grit or finer between coats. Consult product label for additional information.

Application:

- Conventional Spray:
- Air Assisted Airless
- HVLP
- Airless

Cautions:

- Mix container before use
- For industrial use only
- Protect from freezing
- Do not apply in temperatures below 60°F
- Read MSDS for safety information

• Clean-up Information:

For best results, clean all equipment with General Finishes Brush and Gun Cleaner. General clean-up with soap and water recommended. Rinse thoroughly with clean water.

Enduro CLEAR ACRYLIC
012907

NOTICE: All of the above statements, recommendations, suggestions, and data concerning the subject material are based on laboratory results and believed to be reliable. We expressly do not represent, warrant, or guarantee the accuracy, completeness or reliability of same, or the material or the results to be obtained from the use thereof, neither do we warrant that any such use, either alone or in combination with other materials shall be free of the rightful claim of any third party by way of INFRINGEMENT or the like and (THE MANUFACTURER DISCLAIMS ALL WARRANTIES, EXPRESSED OR IMPLIED,) OF MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE.
